

# MasterFlow<sup>®</sup> 622

Heavy duty epoxy resin grout

## DESCRIPTION

**Masterflow 622** is a solvent-free rapid hardening, high strength grout, based on modified epoxy resin and is designed for use as a precision, heavy duty chocking grout for engineering applications. It is supplied as a two component system consisting of epoxy resin, combined with inert fillers and the hardener, to produce a high viscosity flowable liquid grout.

## RECOMMENDED USES

- Machinery with high dynamic loads and vibration.
- Backing of steel liners of ore crushing machinery in mines and quarries.
- In corrosive environments where chemicals, oils and solvents make cementitious grouts unsuitable.
- Production line equipment that must resume operations with minimum downtime.
- Machinery base plates, crane rails, anchor bolts, hold down bolts and heavy equipment where tensile strength greater than cementitious systems can provide are required.

**Masterflow 622** is not recommended where the temperature of the grout after mixing and placing cannot be maintained above 15°C for a period of 48 hours to achieve full cure or where incomplete cure, excessive loads and/or temperatures may induce creep; where required maximum thickness is greater than 50 mm; in this situation additional aggregate may be incorporated (refer to BASF Construction Chemicals); where upper operating temperature is in excess of 130°C; for wet substrates.

## FEATURES AND BENEFITS

- **Resistance to vibration and impact** – Particularly applicable where cycles of compression/ tension make cementitious grouts unsuitable
- **Minimum shutdown** – High early and ultimate strengths
- **Excellent chemical resistance** – Maximum protection against attack from mineral acids,

oils, fats, fuels, and strong alkali and salt solutions and lubricating and hydraulic oils

- **High bond strength** – Tenacious adhesion to prepared surfaces.
- **Supplied in pre-measured kits** – Eliminates the need for complicated on-site measuring and ensured product performance

## PROPERTIES

Compressive strength development (50mm cubes).

Age	23°C
4 hours	69 MPa
6 hours	83 MPa
9 hours	95 MPa
24 hours	105 MPa

Typical test results (after 7 days cure at 23°C ± 2°C)

Compressive Strength (ASTM D 695)	120 MPa
Compressive Modulus	4.0 GPa
Tensile Strength (ASTM D 638)	60 MPa
Linear Shrinkage (ASTM C 531-81)	0.01%
Bond Pull-out	Concrete failed at 2.9 MPa
Setting time @ 23°C	6 hrs

The performance data is typical and based upon controlled laboratory conditions. Actual performance on the job site may vary from these values based on actual site conditions.

Supply Form	
Part A	White Viscous Paste
Part B	Dark blue Heavy Liquid
Mixed	Blue Liquid
Viscosity	30 Pa.s
Density	1690 kg/m <sup>3</sup>

## Pot life

Pot life will vary. As a guide, the pot life of a 10 kg kit, mixed at 23°C would be approx. 30 minutes.



The Chemical Company

# MasterFlow<sup>®</sup> 622

## APPLICATION

For information about application, please obtain a copy of the BASF "Application Guide for Masterflow Epoxy Grouts" from your local representative.

**Masterflow 622** is formulated with a mix ratio of 5:1 by volume, Part A resin to Part B hardener. Units may be split but it is essential to maintain the correct ratio of Part A to Part B. The mix ratio by weight is 10:1 resin to hardener. Remove rim from Part B tin to ensure complete removal of contents. Transfer contents of Part B to Part A container. Mix for 3 minutes using a slow speed electric drill with a flat paddle. Avoid entrapping air. Use without delay.

## ESTIMATING DATA

**Masterflow 622** is available in a two-component kit of 10 kg which yields (when mixed) 5.9 litres.

## PACKAGING

Two-component system available in 10kg kit comprising Part A Resin (9.1 kg) + Part B Hardener (0.9 kg).

## CURING

No damp curing or special curing compounds are required. Cure time will vary depending on quantity

mixed and placed and ambient temperature. Initial set at 23°C will be in 4-6 hours. **Masterflow 622** will be fully cured with maximum physical strength and chemical resistance at 7 days at 23°C. Do not install equipment before full cure has been attained or creep may occur.

Note: Curing rates and strength gain are retarded at lower temperatures - curing will not occur below 5°C.

## SHELF LIFE

**Masterflow 622** has a shelf life of 24 months if stored unopened in original containers at moderate temperatures.

## PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

ID#Masterflow622 ANZ v1.1 0113

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

## BASF Australia Ltd

ABN 62008437867

Construction Chemicals Division

11 Stanton Road Seven Hills, NSW 2147

## Sales Offices:

Sydney, Brisbane, Melbourne, Adelaide, Perth

**Freecall: 1300 227 300**

## BASF Emergency Advice:

1800 803 440 within Australia (24hr)

0800 944 955 within New Zealand

## BASF New Zealand Ltd

45 William Pickering Drive, Albany, Auckland, Phone: 0800 334 877

## BASF WEB SITES

[www.basf-cc.com.au](http://www.basf-cc.com.au)

[www.basf-cc.co.nz](http://www.basf-cc.co.nz)